

RESEARCH & DEVELOPMENT DEPARTMENT					
NOMENCLATURE			PRODUCT SPECIFICATIONS		
S.No.	Properties		UOM	64 GSM	68/70 GSM
1	Substance (A)		g/m ²	± 2.5%	± 2.5%
2	Bulk		cm ³ /g	1.25 ± 0.03	1.25 ± 0.03
3	Breaking Length	MD	meter	5200	5200
		CD		2800	2800
4	Tear Factor	MD	-	48	48
		CD		50	50
5	Bendtsen Smoothne	I Side	ml/min	180 ± 20	180 ± 20
		II Side		90 ± 20	90 ± 20
6	Cobb ₆₀	I Side	g/m ²	26 ± 2	26 ± 2
		II Side		25 ± 2	25 ± 2
7	ISO Brightness, L&W ELREPHO		% ISO	88 ± 1	88 ± 1
8	Opacity (Print),L&W ELREPHO		%	86 ± 1	89 ± 1
9	Passed Wax Pick no.		No.	14A	14A
10	Shade				

SILVER LINE

78/80 GSM	100 GSM	110 GSM	120 GSM
$\pm 2.5\%$	$\pm 2.5\%$	$\pm 2.5\%$	$\pm 2.5\%$
1.25 ± 0.03	1.24 ± 0.03	1.24 ± 0.03	1.24 ± 0.03
5200	5200	5200	5200
2800	2800	2800	2800
48	48	48	48
50	50	50	50
180 ± 20	180 ± 30	180 ± 30	180 ± 30
90 ± 20	110 ± 30	110 ± 30	110 ± 30
26 ± 2	26 ± 2	26 ± 2	26 ± 2
25 ± 2	25 ± 2	25 ± 2	25 ± 2
88 ± 1	88 ± 1	88 ± 1	88 ± 1
91 ± 1	93 ± 1	94 ± 1	95 ± 1
14A	14 A	14 A	14 A

Bright Blue